



# A1030X2N

## Description:

**A1030X2N** is a unique ether-based polyurethane foam grade, designed for your protective packaging challenges. A1030X2N is a standard packaging material that is charcoal in colour and is suitable for a wide variety of interior foam packaging solutions.

## Typical Physical Properties:

PROPERTY	TEST METHOD	TYPICAL RESULTS
DENSITY - (lbs/Ft. <sup>3</sup> )	ASTM D3574	0.90 – 1.00
25% IFD - (lbs)	ASTM D3574	26 - 34
Tensile Strength (min) (lbs/in <sup>2</sup> )	ASTM D3574	10
Elongation % (min)	ASTM D3574	100
Compression Set @ 75% (max)	ASTM D3574	15
Compression Modulus (min)	ASTM D3574	1.8
Hysteresis Loss % (max)	ASTM D3574	40
Resiliency % (min)	ASTM D3574	30

NB: Results are typical and do not encompass the entire range of values.

### IMPORTANT NOTICE REGARDING FLAMMABILITY

Flammability tests are performed under controlled laboratory conditions. Results in no way indicate foam performance in an actual fire. Polyurethane foam should be stored and handled with care. It should be kept away from sources of heat and flame at all times.

Notice: This information is presented in good faith and is believed to be accurate as of the date below. All polyurethane foams including modified foams will burn and generate smoke and gases. Physical properties not to be used as specifications, nominal test numbers fall in the range for the specification in question. Performance conditions and corresponding data refer to typical performance in specific tests, such as CAL TB117-2013, and should not be construed to imply the behaviour of this or any other product under actual fire conditions. All data regarding these products were obtained using specific test methods under controlled laboratory conditions intended to measure performance against specifications. Due to the great number and variety of applications for which VPC Group Inc. are purchased, VPC Group Inc. does not recommend specific applications or assume any responsibility for use, results obtained or suitability for specific applications. This information is given without warranty, representation, inducement or licence of any kind, including but not limited to the implied warranties of merchantability and fitness for a particular use or purpose, except that it is accurate to the best of VPC Group Inc.'s knowledge or obtained from sources believed by VPC Group Inc. to be accurate. VPC Group Inc. does not assume any legal responsibility for use or reliance upon same. Customers are encouraged to conduct their own test.

\*Revised 04/2016

\*This revision supersedes all previous publications

For more information contact:

VPC Group Inc. Corporate Office  
150 Toro Road, Toronto, Ontario, M3J 2A9  
Tel: 416 630 6633 Fax: 416 630 9921  
www.vpcgroup.com

